



UNTREATED PP INK (NPPN)

Main Characteristics

Finish

Gloss

Ink Type

One Pack – Solvent Based

Drying

- Jet dry : 60 °C 5-7 minutes
- Air dry : 15-20 minutes

Thinning

- 10-15 % Retarder 2937

Cleaning

- Cleaner 2940
- For heavy ink stains, Screensolve (SSO038) can be used.

Mesh

- P90-48 to P120-34 Monofilament
- N90-44 to N120-35 Monofilament

Stencil Type

- All solvent resistant direct Emulsion photo-stencils

Recommended

- U017 Diazol Plus Ultra
- FG226 Polyzol Plus S

Coverage & Mesh No.

- 55-65 m²/Kg (Polyester Mesh No. P120-34 or Nylon Mesh No. P120-35)

Application

- Untreated Polypropylene (PP) and Treated Polypropylene (PP)

Caution

- Stir well before use.
- It is advisable that the ink be tested fully prior to printing.

Colours Range

11 Colours : 2 Standard and 9 CMS colours

Features

- Untreated Polypropylene (PP) and Treated Polypropylene (PP).
- Very good abrasion resistance.
- Excellent adhesion and durability.
- All colours are Non-Toxic.

Available Colours

Standard Colours

NPPN100 Black

NPPN200 White

NPPN090 Clear

CMS Base Colours

NPPN327 Yellow GS

NPPN507 Red YS

NPPN560 Magenta

NPPN600 Blue

NPPN347 Yellow RS

NPPN550 Red

NPPN590 Violet

NPPN700 Green

NPPN407 Orange

CHAIYABOON BROTHERS CO.,LTD.

Head Office Pathumthanee 26/9 M.3 Lamlukka Rd, Lamlukka, Pathumthanee 12150, Thailand.

Tel : +662-533-2533, +662-994-5199

Fax : +662-533-2449, +662-994-5180



www.chaiyaboon.com

e-mail: exportmarketing@chaiyaboon.com



รางวัลจรรยาบรรณดีเด่น ทศกาล้ำไพบ

Standard Packing

20 Kg and 1 Kg container.

Safety and Handling

- All colours comply with the following standards : EN71-3, Standard of The European Economic Community and Part1303, Title16, Code of Federal Regulation of U.S.A.
- Whilst working with the ink, the consumption of food and drink, and smoking are not recommended.
- NPPN ink should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Comprehensive information on **the Safety and Handling of NPPN ink** in Chaiyaboon Safety Data Sheet, available on request.

Storage

- NPPN ink should be stored in a sealed container between 5-25 °C.
- Store in a well ventilated place.



NPPN 3-1802

The information and recommendations contained in this Product information sheet, as well as technical advice otherwise given by representatives of our Company, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and or condition that users shall make their own tests to satisfy themselves that they will meet fully their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product information sheet out of date and users are requested to ensure that they follow current recommendations.