



## SVA INK (SVA)

### Main Characteristics

#### Finish

Semi Gloss

#### Ink Type

One Pack – Solvent Based

#### Drying

- Air dry : 10-15 minutes
- Oven stoving : 40-60 °C 2-3 seconds

#### Thinning

- 10-15 % Retarder 6032
- 10-15 % Fast Retarder 2999

#### Cleaning

- Cleaner 2940
- For heavy ink stains, Screensolve (SSO038) can be used.

#### Mesh

- P36-90 to P90-48 Monofilament

#### Stencil Type

- All solvent resistant Emulsion

#### Recommended

- U017 Diazol Plus Ultra
- FG226 Polyzol Plus S

#### Coverage & Mesh No.

- 23-43 m<sup>2</sup>/Kg (Polyester Mesh No. P90-48)

#### Application

- All EVA Substrate

#### Important

- Stir well before use.
- Full test adhesion should be made prior to printing.

#### Colours Range

11 Colours : 2 Standard and 9 CMS colours

### Features

- Suitable for all EVA Substrate.
- Excellent adhesion and flexibility.
- Fast dry.

## CHAIYABOON BROTHERS CO.,LTD.

Head Office Pathumthanee 26/9 M.3 Lamlukka Rd, Lamlukka, Pathumthanee 12150, Thailand.

Tel : +662-533-2533, +662-994-5199

Fax : +662-533-2449, +662-994-5180



[www.chaiyaboon.com](http://www.chaiyaboon.com)

e-mail : [exportmarketing@chaiyaboon.com](mailto:exportmarketing@chaiyaboon.com)



สำนักงานบรรณคดีพิมพ์ ทหารกล้าไทย

### Available Colours

#### Standard Colours

SVA100 Black                      SVA200 White                      SVA090 Extender Base For SVA Ink                      SVA093 Primer For SVA Ink

#### CMS Based Colours

SVA327 Yellow GS                      SVA500 Red YS                      SVA560 Magenta                      SVA600 Blue  
SVA347 Yellow RS                      SVA550 Red BS                      SVA590 Violet                      SVA700 Green  
SVA407 Orange

### Standard Packing

25 Kg, 5 Kg and 1 Kg container.

### Safety and Handling

- All colours comply with the following standards : EN71-3, Standard of The European Economic Community and Part1303, Title16, Code of Federal Regulation of U.S.A.
- Whilst working with the ink, the consumption of food and drink, and smoking are not recommended.
- SVA ink should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Comprehensive information on **the Safety and Handling of SVA ink** in Chaiyaboon Safety Data Sheet, available on request.

### Storage

- SVA ink should be stored in a sealed container and kept between 5-25 °C.
- Store in a well ventilated place.

SVA 3-1802

*The information and recommendations contained in this Product information sheet, as well as technical advice otherwise given by representatives of our Company, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and or condition that users shall make their own tests to satisfy themselves that they will meet fully their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product information sheet out of date and users are requested to ensure that they follow current recommendations.*