



GLOSS – PVC INK (GPY)

Main Characteristics

Finish

Gloss

Ink Type

One Pack – Solvent Based

Drying

- Jet dry : 55-65 °C 15-20 seconds
- Air dry : Not over 10 minutes

Thinning

- 10-15 % Thinner 5099
- 5-10 % Thinner 2938
- Hot shop condition 10-15 % Retarder 2939

Cleaning

- Cleaner 2940
- For heavy ink stains, Screensolve (SSO038) can be used.

Mesh

- P100-40 to P120-34 Monofilament

Stencil Type

- All solvent-resistant direct Emulsion photo-stencils

Recommended

- U017 Diazol Plus Ultra
- FG226 Polyzol Plus S

Coverage & Mesh No.

- 60 m²/Kg (Polyester Mesh No. P120-34)

Application

- PVC, PC, Acrylic, ABS Cellulose Acetate and CAB

Caution

- Stir well before use.
- It is advisable that the ink be tested fully prior to printing.

Colours Range

16 Colours : 7 Standard and 9 CMS

Features

- Printing onto PVC, Polycarbonate/PC, Acrylic, ABS, Cellulose Acetate and CAB.
- Excellent flexibility and chemical resistance.
- Fast drying and high gloss.
- Excellent light fast and weather resistance.

Available Colours

Standard Colours

GPY100 Black	GPY337 Light Chrome	GPY527 Scarlet	GPY724 Bright Green
GPY200 White	GPY407 Orange	GPY723 Brilliant Green	GPY090 Clear

CMS Base Colours

GPY327 Yellow GS	GPY507 Red YS	GPY560 Magenta	GPY600 Blue
GPY347 Yellow RS	GPY550 Red BS	GPY590 Violet	GPY700 Green
GPY447 Orange			

CHAIYABOON BROTHERS CO., LTD.

26/17 M.3 Lumlukka Road, Lat Sawai, Lumlukka, Pathum Thani 12150 Thailand
 Tel : +662-533-2533, +662-994-5199
 Fax : +662-994-2449, +662-994-5180

SUPERB SUPPLIES SERVICE FOR SCREEN AND DIGITAL

www.chaiyaboon.com
 e-mail : sale_cb@cbg.in.th



Standard Packing

1 Kg container.

Safety and Handling


- All other colours comply with the following standards : EN71-3, Standard of The European Economic Community and Part1303, Title16, Code of Federal Regulation of U.S.A.
- Whilst working with the ink, the consumption of food and drink, and smoking are not recommended.
- GPY ink should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Comprehensive information on **the Safety and Handling of GPY ink** in Safety Data Sheet, available on request.

Storage

- GPY ink should be stored in a sealed container between 5-25 °C.
- Store in a well ventilated place.

Certified Standards

- GPY ink is made by Kulwong Co., Ltd. with ISO 9001/ISO 14001/BS OHSAS 18001 & TIS 18001 Certified by TUV NORD (Thailand) Ltd.



GPY 3-1903