



POLYZOL PLUS S (FG224)

Main Characteristics

Type

One pot/Purple colour

Solid content (unsensitized) %

38 %

Preparing the Screen

- New screen should be abraded with Screenprep (SPR034) before use for optimum stencil durability.
- Degreasing the screen, use Degreaser Plus (P-6419)

Coating

Manual

- Apply one or two coats of Polyzol Plus S, wet on wet, to the print side of screen.
- Apply one or two coats of this emulsion, wet on wet, to the squeegee side of screen.
- If a higher build of Polyzol Plus S is required extra coats should be applied, wet on wet to the squeegee side.

Automatic

- When using an automatic coating machine, a simultaneous single coat on each side of the screen is recommended.
- If higher builds are required, extra coats should be applied to the squeegee side of the screen.

Drying

Put coated screen in hot air oven with squeegee side up. Do not exceed 40 °C.

Table of Exposure Guide

Light Source	Distance	Length of Exposure Time*
3000W Metal Halide	100 cm.	30-40 Seconds

* Using 120-34Y Polyester Screen Mesh.

Developing

Place the screen in washout booth and gently spray both sides, increase the spray pressure slightly. Continue developing until or parts of the image appear clean and sharp.

Spotting

Check for pinholes or blemishes. Spot out with a suitable filler use Screen Filler (22997)

Reclaiming the Screen

- Screenstrip Powder (SST002) thoroughly to both side of the stencil.
- Screenstrip Liquid (SST004) thoroughly to both side of the stencil.

Recommended inks

- Solvent based ink and UV based ink.

Caution

Special safelight is not essential, but yellow or weak illumination is desirable.

CHAIYABOON BROTHERS CO., LTD.

26/17 M.3 Lumlukka Road, Lat Sawai, Lumlukka, Pathum Thani 12150 Thailand
 Tel : +662-533-2533, +662-994-5199
 Fax : +662-994-2449, +662-994-5180

SUPERB SUPPLIES SERVICE FOR SCREEN AND DIGITAL

www.chaiyaboon.com
 e-mail : sale_cb@cbg.in.th



Features

- One pot photopolymer emulsion.
- Excellent latitude, resolution and definition.
- Fast exposure.
- For high quality graphic printing.

Standard Packing

Emulsion : 5 Kg and 1 Kg

Safety and Handling

- Is free from any toxic, carcinogenic, mutagenic and reprotoxic chemicals.
- Does not have a flashpoint and is, therefore, exempt from the Highly Flammable Liquid Regulations.
- Should be stored away from children.
- Comprehensive information on *the Safety and Handling of Polyzol Plus S* in Safety Data Sheet.

Storage

- FG224 should be stored in a cool temperature as possible not below 0 °C or over 25 °C.
- FG224 can be stored for 15 months.
- Screen coated in advance must be stored at 20 °C and in complete darkness.
- With longer storage of pre-coated screen, the emulsion can absorb moisture from the environment. It is therefore advisable to dry again prior to exposing.

Certified Standards

- FG224 is made by Kulwong Co., Ltd. with ISO 9001/ISO 14001/BS OHSAS 18001 & TIS 18001 Certified by TUV NORD (Thailand) Ltd.

FG224 2-1902