



OPAQUE INK (TP)

Main Characteristics

Ink Type

One Pack / Water-Based

Drying

- Jet dry : 3-5 minutes
- Air dry : 10-15 minutes
- Final step oven : 150 °C 3 minutes

Thinning

- 5-10 % Water

Cleaning

- Water
- For heavy ink stains, Screensolve (SSO038) can be used.

Mesh

- P21-140 to P48-70 Monofilament

Stencil Type

- All water resistant direct Emulsion photo-stencils

Recommended

- T326 Diazol Tex
- FT426 Polyzol Tex

Application

- Light and dark shade fabrics made wholly or partly of natural fibres such as cotton

Important

- Stir well before use.
- It is advisable that the ink be tested fully prior to printing.

Colours Range

15 Colours : 15 Standard colours

Features

- Suitable for light and dark shade fabrics made wholly or partly of natural fibres such as cotton.
- High opacity.
- Long lasting colour brightness.
- Excellent wash resistance.

Available Colours

Standard Colours

TP100 Black	TP400 Light Orange	TP624 Royal Blue	TP791 Light Brown
TP200 White	TP520 Scarlet	TP645 Navy Blue	TP861 Gold
TP330 Light Chrome	TP590 Violet	TP720 Brilliant Green	TP862 Silver
TP340 Mid Chrome	TP623 Mid Blue	TP721 Bright Green	TP090 Clear

Standard Packing


50 Kg, 25 Kg, 4 Kg, 1 Kg and 500 g container.

CHAIYABOON BROTHERS CO., LTD.

26/17 M.3 Lumlukka Road, Lat Sawai, Lumlukka, Pathum Thani 12150 Thailand
 Tel : +662-533-2533, +662-994-5199
 Fax : +662-994-2449, +662-994-5180

SUPERB SUPPLIES SERVICE FOR SCREEN AND DIGITAL

www.chaiyaboon.com
 e-mail : sale_cb@cbg.in.th



Safety and Handling

- All colours comply with the following standards : EN71-3, Standard of The European Economic Community and Part1303, Title16, Code of Federal Regulation of U.S.A.
- Whilst working with the ink, the consumption of food and drink, and smoking are not recommended.
- TP ink should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Comprehensive information on **the Safety and Handling of TP ink** in Safety Data Sheet, available on request.

Storage

- Storage temperature should not be over 40 °C. It should be stored in a dry location with good ventilation and away from heat or ignition sources.
- When stored under these conditions, It is expected to have a shelf-life of 24 months from the date of manufacture.
- Close the bottle tightly after every use.

Certified Standards

- TP ink is made by Kulwong Co., Ltd. with ISO 9001/ISO 14001/BS OHSAS 18001 & TIS 18001 Certified by TUV NORD (Thailand) Ltd.

