



## SCRATCH REMOVABLE INK (SCR)

### Main Characteristics

#### Finish

Satin

#### Ink Type

One Pack – Solvent Based

#### Drying

- Jet dry : 55–65 °C 20 seconds
- Air dry : 10–15 minutes

#### Thinning

- 5–10 % Thinner 6032
- 5–10 % Thinner 2938
- Hot shop condition 5–10 % Retarder 2939

#### Cleaning

- Cleaner 2940
- For heavy ink stains, Screensolve (SSO038) can be used.

#### Mesh

- P61–34 to P90–40 Monofilament

#### Stencil Type

- All solvent-resistant direct Emulsion photo-stencils

#### Recommended

- U017 Diazol Plus Ultra
- FG226 Polyzol Plus S

#### Coverage & Mesh No.

- 35 m<sup>2</sup>/Kg (Polyester Mesh No. P77–48)

#### Application

- Lottery tickets and Promotional Card

#### Important

- Stir well before use.
- It is advisable that the ink be tested fully prior to printing.

#### Colours Range

1 Colour : 1 Standard colour

### Features

- Printing onto Lottery Tickets and Promotional Card.
- Remove with a coin or fingernail.
- SCR is are opaque ink.

### Available Colours

#### Standard Colour

SCR862 Silver

### Standard Packing

1 Kg container.

## CHAIYABOON BROTHERS CO.,LTD.

Head Office Pathumthanee 26/9 M.3 Lamukka Rd, Lamukka, Pathumthanee 12150, Thailand.

Tel : +662-533-2533, +662-994-5199

Fax : +662-533-2449, +662-994-5180

[www.chaiyaboon.com](http://www.chaiyaboon.com)

e-mail : [exportmarketing@chaiyaboon.com](mailto:exportmarketing@chaiyaboon.com)



สำนักงานบรรณคดี ศูนย์การค้าไทย

**Safety and Handling**

- SCR ink comply with the following standards : EN71-3, Standard of The European Economic Community and Part1303, Title16, Code of Federal Regulation of U.S.A.
- Whilst working with the ink, the consumption of food and drink, and smoking are not recommended.
- SCR ink should be used with care. Wear suitable PPE, for example, appropriate gloves and safety glasses.
- Comprehensive information on **the Safety and Handling of SCR ink** in Chaiyaboon Safety Data Sheet, available on request.

**Storage**

- SCR ink should be stored in a sealed container between 5-25 °C.
- Store in a well ventilated place.



SCR 3-1802

*The information and recommendations contained in this Product information sheet, as well as technical advice otherwise given by representatives of our Company, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and or condition that users shall make their own tests to satisfy themselves that they will meet fully their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product information sheet out of date and users are requested to ensure that they follow current recommendations.*